

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 114 842 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
11.07.2001 Bulletin 2001/28

(51) Int Cl.⁷: **C08G 65/32, C08G 65/00**

(21) Application number: **00128069.2**

(22) Date of filing: **21.12.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **04.01.2000 IT MI200003**

(71) Applicant: **Ausimont S.p.A.**
20121 Milano (IT)

(72) Inventors:
• **Tonelli, Claudio**
20099 Sesto S. Giovanni (MI) (IT)
• **Russo, Antonio**
20100 Milano (IT)
• **Strepparola, Ezio**
24047 Treviglio (BG) (IT)

(74) Representative: **Sama, Daniele, Dr.**
Sama Patents
Via Morgagni, 2
20129 Milano (IT)

(54) **A process for the preparation of perfluoropolyoxyalkylenes with hydroxyl end groups**

(57) A process for preparing perfluoropolyoxyalkylenes with hydroxyl end groups having structure:



wherein:

T_1, T_2 , are selected from $-CH_2OH$, $-F$, $-CF_3$, $-CF_2CF_3$ with the proviso that at least one of T_1 and T_2 is $-CH_2OH$;

W_1 and W_2 are selected from F , CF_3 ;

R_f is a perfluoropolyoxyalkylene chain having a number average molecular weight 500-10,000 comprising one or more units of the type $-CF_2CF_2O-$, $-CF_2O-$, $-C_3F_6O-$, $-CF_2(CF_2)_zCF_2O-$ ($z=1,2$);

$-CR_4R_5CF_2CF_2O-$ with R_4 and R_5 selected from H , Cl , perfluoroalkyl group;

a) adding an ester precursor having structure (I) and T_1, T_2 end groups selected from $-F$, $-CF_3$, $-CF_2CF_3$, $-COOR$ (R =linear or branched alkyl group having a number of C atoms from 1 to 5), with the proviso that at least one of T_1 and T_2 is $-COOR$, in a reaction mixture formed by:

- an inert or protic reaction solvent;
- a reducing agent selected from metal hydrides;
- an unreactive organic base with respect to the ester;

b) hydrolysis of the product obtained in step a) for obtaining the compounds of structure (I) with at least a $-CH_2OH$ end group.

said process comprising the following steps:

EP 1 114 842 A2

Description

[0001] The invention relates to a process for the preparation of perfluoropolyoxyalkylenes functionalized with hydroxyl end groups.

[0002] Specifically the invention relates to a process for the preparation of monofunctional and bifunctional perfluoropolyoxyalkylenes having end groups of -CH₂OH type starting from the corresponding perfluoropolyoxyalkylenes having -COOR end groups (R=C₁-C₅ alkyl). Said process has a higher productivity since in the reduction reaction a lower amount of reducing agent is used. Further a lower hydrogen development is noticed during the reaction. This makes the process better controllable from the industrial safety point of view and economically cheaper.

[0003] Monofunctional and bifunctional perfluoropolyoxyalkylenes having hydroxyl end groups of the -CH₂OH type are known in the prior art.


[0004] These compounds are described, for example, in USP 3,766,251 and USP 3,810,874 and they can be used for example as lubricants for magnetic discs or as macromonomers for the preparation of polyurethane, polyester, polyether copolymers, epoxy resins, etc.

[0005] The perfluoropolyethers with hydroxyl end groups can be prepared by reduction of the corresponding ester precursors, i.e. starting from perfluoropolyethers having one or two end groups -COOR wherein R is a linear or branched C₁-C₅ alkyl. Said process is described for example in the patents GB 1,309,401, USP 3,847,978.

[0006] Generally in the known processes, the reduction reaction is carried out by using reducing agents in inert solvents. Among the reducing agents metal hydrides, such as for example lithium-aluminum hydride (LiAlH₄), dissolved in inert solvents such as tetrahydrofuran, diglyme or dioxane can be mentioned; preferably as reducing agent sodium-boron hydride (NaBH₄) in the above mentioned inert solvents or in protic solvents such as methanol, ethanol, is used.

[0007] When NaBH₄ is used as reducing agent, the stoichiometry of the reduction reaction of the ester precursor to the corresponding perfluoropolyether with hydroxyl end groups CH₂OH, implies the use of two equivalents of ester by mole of NaBH₄ and it does not involve hydrogen formation.

[0008] The process can be schematized with the following reactions, by using sodium-boron hydride as reducing agent and a bifunctional ester with both end groups -COOC₂H₅ as precursor:




[0009] However tests carried out by the Applicant

show (see the comparative Examples) that said reduction reaction in order to reach an almost total conversion (higher than 99%), requires a large excess of reducing agent NaBH₄, generally higher than 60% with respect to the stoichiometric value. Another drawback is that during the reduction step a remarkable hydrogen amount develops, in the range 1.5 - 2 moles of hydrogen for each equivalent of ester. The large excess of reducing agent necessary for the reduction reaction and the remarkable volume of hydrogen developed during the reaction, result critical both from an economic point of view, due to the cost of the reducing agent, and from a point of view of to the process safety in an industrial plant. In fact the gaseous effluents must be diluted with large volumes of inert gas in order to bring the composition of the gaseous mixture, in particular the hydrogen concentration, under the inflammability and explosiveness limits (lower than 4% by volume).

[0010] The need was therefore felt to prepare functional perfluoropolyethers having -CH₂OH end groups by a cheaper process from the economic point of view, furthermore characterized by a greater production combined with a greater reliability from the industrial safety point of view.

[0011] The Applicant has surprisingly and unexpectedly found that the reduction reaction to obtain perfluoropolyethers having hydroxyl -CH₂OH end groups, starting from the corresponding ester precursors, can be advantageously carried out by adding in the reaction mixture besides the reducing agent, an organic base. It has been unexpectedly found that the presence of this organic base allows to carry out the reducing reaction by using a small excess of the reducing agent with respect to the stoichiometric amount, generally lower than 15%, and surprisingly that it inhibits the hydrogen development during the process.

[0012] It is therefore an object of the present invention a process for obtaining monofunctional and bifunctional perfluoropolyoxyalkylenes having hydroxyl end groups with structure:



wherein:

T₁, T₂, equal to or different from each other, are selected from end groups of the -CH₂OH, or -F, -CF₃, -CF₂CF₃ type with the proviso that at least one of T₁ and T₂ is -CH₂OH;

W₁ and W₂, equal to or different from each other, are F, CF₃; R_f is a perfluoropolyoxyalkylene chain having a number average molecular weight 500-10,000 comprising one or more units of the -CF₂CF₂O-, -CF₂O-, -C₃F₆O-, -CF₂(CF₂)_zCF₂O-, -CR₄R₅CF₂CF₂O- type;

wherein: z is an integer equal to 1 or 2;

R_4 and R_5 , equal to or different from each other, are selected from H, Cl, linear or branched perfluoroalkyl groups having a number of C atoms from 1 to 4;

said units being statistically distributed along the perfluoropolyoxyalkylene chain;

said process comprising the following steps:

a) adding, under inert gas atmosphere, an ester precursor having structure (I) and T_1 , T_2 end groups, equal to or different from each other, selected from -F, -CF₃, -CF₂CF₃, -COOR (R=linear or branched alkyl group having a number of C atoms from 1 to 5), with the proviso that at least one of T_1 and T_2 is -COOR, in a reaction mixture formed by:

- an inert or protic reaction solvent;
- a reducing agent selected from the metal hydride class;
- a non reactive organic base with respect to the ester;

b) hydrolysis of the product obtained in step a) for obtaining the compounds of structure (I) with at least a -CH₂OH end group.

[0013] The organic bases used in the process of the present invention are selected from alcoholates and thioalcoholates of alkaline or alkaline-earth metals, having alkyl, cycloaliphatic, aromatic chain or combinations thereof; or nitrogenous bases which do not give condensation reactions with the fluorinated ester, such as for example amidation reactions. The following bases are preferably used: sodium or potassium alcoholates such as for example potassium *tert*-butylate or sodium ethylate, more preferably sodium ethylate; in the class of the nitrogenous bases, alkyl, cycloaliphatic and aromatic tertiary amines, such as for example triethylamine, diazabicyclo-octane (DABCO), pyridine, can be mentioned. Also a mixture of the above mentioned organic bases can be used. Preferably as organic bases the class of the above mentioned alcoholates is used.

[0014] As solvents of the reaction inert solvents, such as for example, tetrahydrofuran, diglyme, dioxane or protic solvents such as for example methanol, ethanol, isopropanol, isobutanol or mixtures thereof, preferably ethanol, etc., can be used. Also mixtures of inert solvents and protic solvents can be used.

[0015] As reducing agents metal hydrides, such as for example lithium-aluminum hydride (LiAlH₄), sodium-boron hydride (NaBH₄), lithium-boron hydride, etc., dissolved in the above mentioned reaction solvents, can be used. Preferably as reducing agent, sodium-boron hydride is used.

[0016] In formula (I) R_f preferably comprises the following repeating units statistically distributed along the polymer chain:

- (CF₂CF₂O) - , - (CFYO) - wherein Y is equal to F or CF₃,
- (C₃F₆O) - ,
- (CF₂(CF₂)_zO) - wherein z is an integer equal to 2 or 3,
- CR₄R₅CF₂CF₂O - wherein R_4 and R_5 , equal to or different from each other are selected from H, Cl or perfluoroalkyl group having 1-4 C atoms.

In particular the following fluoropolyether R_f can be mentioned as the preferred ones:

(A) - (CF₂CF (CF₃) O)_a (CFYO)_b -

wherein Y is F or CF₃; a and b are integers such that the molecular weight is in the above mentioned range: a/b is in the range 10-100;

or the repeating units mentioned in (A) can be linked as follows:

- (CF₂CF (CF₃) O)_a (CFYO)_b-CF₂(R'_f)_xCF₂-O- (CF₂CF (CF₃) O)_a (CFYO)_b- wherein R'_f is a fluoroalkylene group from 1 to 4 C;

(B) - (CF₂CF₂O)_c (CF₂O)_d (CF₂ (CF₂)_zO)_h -

wherein c, d and h are integers such that the molecular weight is in the above mentioned range; c/d is in the range 0.1-10; h/(c+d) is in the range 0-0.05, z has the above mentioned value, h can also be equal to 0;

(C) - (CF₂CF (CF₃) O)_e (CF₂CF₂O)_f (CFYO)_g -

wherein Y is F or CF₃; e, f, g are integers such that the molecular weight is in the above mentioned range; e/ (f+g) is in the range 0.1-10, f/g is in the range 2-10;

(D) - (CF₂ (CF₂)_zO)_s -

wherein s is an integer such as to give the above mentioned molecular weight, z has the already defined meaning;

(E) - (CR₄R₅CF₂CF₂O)_j -

wherein R_4 and R_5 are equal to or different from each other and selected from H, Cl or perfluoroalkyl group, for example with 1-4 C atoms, j' being an integer such that the molecular weight is the above mentioned one;

said unit inside the fluoropolyoxyalkylene chain can be linked each other as follows:

- (CR₄R₅CF₂CF₂O)_p - R'_f - O - (CR₄R₅CF₂CF₂O)_q -

wherein R'_f is fluoroalkylene group, for example from 1 to 4 C, p' and q' are integers such that the molecular weight is the above mentioned one;

(F) - (CF(CF₃)CF₂O)_{j''} -

j'' being an integer such as to give the above mentioned molecular weight.

(A) and (B) are particularly preferred structures.

[0017] These structures comprising the mentioned repeating units and the methods for the preparation thereof are described in the patents GB 1,104,482, USP 3,242,218, USP 3,665,041, USP 3,715,378, USP 3,665,041, EP 148,482, USP 4,523,039, USP

5,144,092, and for the functional derivatives see USP 3,810,874 and the patents mentioned in the prior art. All these patents are incorporated herein by reference.

[0018] The reaction for obtaining the invention compounds of

formula (I) is preferably carried out at temperatures comprised between 0°C and the boiling temperature of the solvent, preferably between 0°C and 30°C.

[0019] In the reduction process of the present invention the reducing agent, preferably sodium-boron hydride, is used, in an amount in the range 0.1-15% by weight based on the solvent weight.

[0020] The used base amount can range between 0.1 and 100% by moles with respect to the reducing agent, preferably between 2 and 15% by moles, still more preferably between 5 and 15% by moles. The reducing agent excess, preferably sodium-boron hydride, necessary for reducing the ester, is in the range 0-30% with respect to the stoichiometric value, preferably 10-20%.

[0021] The product hydrolysis and isolation step (step b) is carried out according to known methods in the prior art. Generally hydrolysis is carried out by slowly adding the reaction product obtained in step a) to an aqueous HCl solution, preferably at a 5-10% concentration by weight, in an equimolar amount with respect to the initially fed ester. The addition of the products of step a) to the acid solution is carried out gradually due to the hydrogen development deriving from the hydrolysis of the possible excess of the unreacted reducing agent. Alternatively, the hydrolysis step can be carried out by using water in a ratio by weight 2:1 with respect to the initially fed ester. Further aqueous washings can be optionally made at the end of step b) to completely eliminate the inorganic salts from the reduced fluorinated product.

[0022] The hydrolysis of the reaction products of step a) can be also carried by directly feeding the hydrolyzing solution or the water of step b) in the reaction mixture of step a).

[0023] With the process of the present invention it is possible to obtain an almost total conversion of the starting ester, higher than 99%, by using a reducing agent excess in the range 0-30% with respect to the stoichiometric value. Said excess of reducing agent is clearly lower than that used in the conventional processes of the prior art, where an excess higher than 60% is necessary. The selectivity of the invention process is higher than 99%.

[0024] The use of a lower amount of reducing agent leads, as a consequence, to a reduction of the amount of the necessary solvent in the mixture and therefore to a higher production with respect to the processes of the prior art, making the process more profitable from the economic and industrial point of view. Furthermore, the hydrogen development during the reaction is practically negligible or however remarkably reduced, of about 10 times, with respect to the reaction carried out in absence of organic base. This makes the process of the invention

more controllable from a technological and therefore from a safety point of view. The planning and running of the industrial plant are simplified since the need to dilute, with large volumes of inert gas, the effluents in order to bring the composition under the inflammability and explosiveness limits of the gaseous mixture containing hydrogen, is eliminated. This avoids the need to foresee and set up a suitable unit of treatment of these effluents in order not to pollute the environment with reactants, solvents and/or reaction intermediates.

[0025] The use of a lower production ratio by weight between reducing agent and obtained product of structure I, up to a reduction of about 40% in the case of sodium-boron hydride, allows, the operating conditions being equal, to reduce the solvent amount necessary to carry out the reduction. There is therefore an increased production as well as a saving of raw materials.

[0026] The present invention will be better illustrated by the following Examples, which have a merely indicative but not limitative purpose of the scope of the invention itself.

EXAMPLES

EXAMPLE 1

[0027] A 3 l jacketed reactor, equipped with mechanical stirrer and directly connected to a volumetric gas reader, is charged with ethanol (770 g), sodium ethoxide (10 g, 0.147 moles) and NaBH₄ (56 g, 1.47 moles). The reaction mixture is then heated to 10°C, maintaining the temperature in external jacket at 8°C. 400 g (0.7 equivalents) of a perfluoropolyoxyalkylene biester of general formula C₂H₅OOC-CF₂O (CF₂CF₂O)_n- (CF₂O)_aCF₂-COOC₂H₅ having a number average molecular weight Mn=1121 and an average equivalent weight Ew=573, are fed, under stirring, with a 200 g/h flow-rate.

[0028] By maintaining the temperature (8°C) in the jacket constant for the whole feeding period (2h), the temperature inside the reactor rises up to 15°C. During the reaction 0.9 litres of H₂ develop. At the end of the feeding the unreacted sodium-boron hydride is titrated, and contemporaneously the intermediate boric esters are hydrolyzed, by feeding them in 1000 g of an aqueous HCl solution at 10% by weight, volumetrically measuring the developed hydrogen moles. The developed hydrogen volume resulted equal to 99.8 litres (4.45 moles), equivalent to 42.3 g (1.11 moles) of unreacted NaBH₄. During the reaction an excess of NaBH₄ equal to 2.9% with respect to the stoichiometric value has therefore been consumed.

[0029] After the addition to the HCl solution, the reaction mixture is left under stirring at room temperature for about one hour. The phases are then separated and the organic phase is stripped at 60°C/1 mmHg and then analyzed by IR and NMR. The analyses are in agreement with the total reduction of the ester.

EXAMPLE 2

[0030] By using the equipment and the procedures reported in Example 1, ethanol (400 g), potassium tert-butylate (6 g, 0.05 moles) and NaBH₄ (32 g, 0.84 moles) are introduced in the reactor. 400 g (0.38 equivalents) of a perfluoropolyoxyalkylene biester of general formula C₂H₅OOC-CF₂O(CF₂CF₂O)_p-(CF₂O)_qCF₂-COOC₂H₅ having a number average molecular weight Mn=2045 and an average equivalent weight Ew=1042, are fed, under stirring, with a 400 g/h flow-rate.

[0031] By maintaining the temperature (8°C) in the jacket constant for the whole feeding period (1h), the temperature inside the reactor rises up to 13°C. During the reaction 1.2 litres of H₂ develop. At the end of the feeding the unreacted sodium-boron hydride is titrated, and contemporaneously the intermediate boric esters are hydrolized, by feeding 1000 g of an aqueous HCl solution at 10% by weight, volumetrically measuring the developed hydrogen moles. The developed hydrogen volume resulted equal to 57 litres (2.5 moles), equivalent to 23.75 g (0.625 moles) of unreacted NaBH₄. During the reaction an excess of NaBH₄ equal to 7% with respect to the stoichiometric value has therefore been consumed.

EXAMPLE 3

[0032] By using the equipment and the procedures of Example 1, ethanol (103 g) and under stirring metal sodium (0.42 g; 0.2 moles) are introduced in the reactor. When the metal sodium disappears, NaBH₄ (8.3 g, 0.22 moles) is then introduced in the reactor. 300 g (0.288 equivalents) of a perfluoropolyoxyalkylene biester of general formula C₂H₅OOC-CF₂O(CF₂CF₂O)_p-(CF₂O)_qCF₂-COOC₂H₅ having a number average molecular weight Mn=2045 and an average equivalent weight Ew=1042, are fed, under stirring, with a 150 g/h flow-rate.

[0033] By maintaining the temperature (5°) in the jacket constant for the whole feeding period (2h), the temperature inside the reactor rises up to 12°C. During the reaction 0.25 litres of H₂ develop. At the end of the feeding the unreacted sodium-boron hydride is titrated, and contemporaneously the intermediate boric esters are hydrolized, feeding 1000 g of an aqueous HCl solution at 10% by weight, volumetrically measuring the developed hydrogen moles. The developed hydrogen volume resulted equal to 6.7 litres (0.299 moles), equivalent to 2.8 g (0.074 moles) of unreacted NaBH₄. During the reaction an excess of NaBH₄ equal to 1.8% with respect to the stoichiometric value has therefore been consumed.

EXAMPLE 4

[0034] By using the equipment and the procedures reported in Example 1, ethanol (102 g), sodium ethylate

(1.5 g, 0.022 moles) and NaBH₄ (8.5 g, 0.23 moles) are introduced in the reactor. 200 g (0.299 equivalents) of a perfluoropolyoxyalkylene biester of general formula C₂H₅OOC-CF₂O(CF₂CF₂O)_p-(CF₂O)_qCF₂-COOC₂H₅ having a number average molecular weight Mn=1311 and an average equivalent weight Ew=668, are fed, under stirring, with a 150 g/h flow-rate.

[0035] By maintaining the temperature (5°) in the jacket constant for the whole feeding period (1.3 h), the temperature inside the reactor rises up to 12°C. During the reaction 0.3 litres of H₂ develop. At the end of the feeding the unreacted sodium-boron hydride is titrated, and contemporaneously the intermediate boric esters are hydrolized, feeding 1000 g of an aqueous HCl solution at 10% by weight, volumetrically measuring the developed hydrogen moles. The developed hydrogen volume resulted equal to 6.9 litres (0.308 moles), equivalent to 2.88 g (0.77 moles) of unreacted NaBH₄. During the reaction an excess of NaBH₄ equal to 2.2% with respect to the stoichiometric value has therefore been consumed.

EXAMPLE 5 (comparative)

[0036] By using the equipment and the procedures reported in Example 1, the same testing is repeated in absence of the sodium ethoxylate base. 400 g (0.7 equivalents) of a perfluoropolyoxyalkylene biester of general formula C₂H₅OOC-CF₂O(CF₂CF₂O)_p-(CF₂O)_qCF₂-COOC₂H₅ having a number average molecular weight Mn=1121 and an average equivalent weight Ew=573, are then fed with a 200 g/h flow-rate.

[0037] By maintaining the temperature (8°C) in the jacket constant for the whole feeding period (2 h), the temperature inside the reactor rises up to 17°C. During the reaction hydrogen development equal to 28 litres is observed. At the end of the feeding the unreacted sodium-boron hydride is titrated, and contemporaneously the intermediate boric esters are hydrolized, feeding 1000 g of an aqueous HCl solution at 10% by weight, volumetrically measuring the developed hydrogen moles. The developed hydrogen volume resulted equal to 72 litres (3.2 moles), equivalent to 30 g (0.8 moles) of unreacted NaBH₄. During the reaction an excess of NaBH₄ equal to 92% with respect to the stoichiometric value has therefore been consumed.

EXAMPLE 6 (comparative)


[0038] By using the equipment and the procedures reported in Example 2, the same testing is repeated in absence of the potassium tert-butoxylated base. 400 g (0.38 equivalents) of a perfluoropolyoxyalkylene biester of general formula C₂H₅OOC-CF₂O(CF₂CF₂O)_p-(CF₂O)_qCF₂-COOC₂H₅ having a number average molecular weight Mn=2045 and an average equivalent weight Ew=1042, are then fed with a 400 g/h flow-rate.

[0039] By maintaining the temperature (8°C) in the

jacket constant for the whole feeding period (2 h), the temperature inside the reactor rises up to 18°C. During the reaction hydrogen development equal to 13 litres is observed. At the end of the feeding the unreacted sodium-boron hydride is titrated, and contemporaneously the intermediate boric esters are hydrolized, feeding 1000 g of an aqueous HCl solution at 10% by weight, volumetrically measuring the developed hydrogen moles. The developed hydrogen volume resulted equal to 45 litres (2 moles), equivalent to 19 g (0.5 moles) of unreacted NaBH₄. During the reaction an excess of NaBH₄ equal to 78% with respect to the stoichiometric value has therefore been consumed.

Claims

1. A process for preparing monofunctional and bifunctional perfluoropolyoxyalkylenes having hydroxyl end groups having structure:



wherein:

T₁, T₂, equal to or different from each other, are selected from end groups of the -CH₂OH, or -F, -CF₃, -CF₂CF₃ type with the proviso that at least one of T₁ and T₂ is -CH₂OH;

W₁ and W₂, equal to or different from each other, are F, CF₃;

R_f is a perfluoropolyoxyalkylene chain having a number average molecular weight 500-10,000 comprising one or more units of the type -CF₂CF₂O-, -CF₂O-, -C₃F₆O-, -CF₂(CF₂)_zCF₂O-, -CR₄R₅CF₂CF₂O-;

wherein:

z is an integer equal to 1 or 2;

R₄ and R₅, equal to or different from each other, are selected from H, Cl, linear or branched perfluoroalkyl group having a number of C atoms from 1 to 4;

said units being statistically distributed along the perfluoropolyoxyalkylene chain;

said process comprising the following steps:

- a) adding, under inert gas atmosphere, an ester precursor having structure (I) and T₁, T₂ end groups, equal to or different from each other, selected from -F, -CF₃, -CF₂CF₃, -COOR (R=linear or branched alkyl group having a number of C atoms from 1 to 5), with the proviso that at least one of T₁ and T₂ is -COOR, in a reaction mixture formed by:

- an inert or protic reaction solvent;
- a reducing agent selected from the metal hydride class;
- an unreactive organic base with respect to the ester;

b) hydrolysis of the product obtained in step a) for obtaining the compounds of structure (I) with at least a

- CH₂OH end group.

2. A process according to claim 1, wherein the organic base is selected from alcoholates and thioalcoholates of alkaline or alkaline-earth metals, having alkyl, cycloaliphatic, aromatic chain or combinations thereof; nitrogenous bases selected from alkyl, cycloaliphatic and aromatic tertiary amines, such as triethylamine, diazabicyclo-octane (DABCO), pyridine.

3. A process according to claim 2, wherein the organic base is selected from sodium or potassium alcoholates such as potassium *tert*-butylate or sodium ethylate, preferably sodium ethylate.

4. A process according to claims 1-3, wherein the solvents of the reaction are selected from inert solvents, such as tetrahydrofuran, diglyme, dioxane; protic solvents such as methanol, ethanol, isopropanol, isobutanol, preferably ethanol; mixtures of inert solvents and protic solvents.

5. A process according to claims 1-4, wherein the reducing agents are selected from metal hydrides, such as lithium-aluminum hydride (LiAlH₄), sodium-boron hydride (NaBH₄), lithium-boron hydride.

6. A process according to claims 1-5, wherein R_f comprises the following repeating units statistically distributed along the polymer chain:

- (CF₂CF₂O) - , - (CFYO) - wherein Y is equal to F or CF₃,
- (C₃F₆O) - ,
- (CF₂(CF₂)_zO) - wherein z is an integer equal to 2 or 3,
- CR₄R₅CF₂CF₂O - wherein R₄ and R₅, equal to or different from each other are selected from H, Cl, perfluoroalkyl group having 1-4 C atoms.

7. A process according to claim 6, wherein R_f is selected from:

(A) - (CF₂CF(CF₃)O)_a(CFYO)_b-
wherein Y is F or CF₃; a and b are integers such that the molecular weight is in the above mentioned range: a/b is in the range 10-100;

or the repeating units mentioned in (A) can be linked as follows:

- $(\text{CF}_2\text{CF}(\text{CF}_3)\text{O})_a(\text{CF}_2\text{O})_b - \text{CF}_2(\text{R}'_f)_x\text{CF}_2$
- $\text{O}-(\text{CF}_2\text{CF}(\text{CF}_3)\text{O})_a(\text{CF}_2\text{O})_b-$
wherein R'_f is a fluoroalkylene group from 1 to 4 C;

(B) - $(\text{CF}_2\text{CF}_2\text{O})_c(\text{CF}_2\text{O})_d(\text{CF}_2(\text{CF}_2)_z\text{O})_h-$
wherein c, d and h are integers such that the molecular weight is in the above mentioned range; c/d is in the range 0.1-10; h/(c+d) is in the range 0-0,05, z has the above mentioned value, h can also be equal to 0;

(C) - $(\text{CF}_2\text{CF}(\text{CF}_3)\text{O})_e(\text{CF}_2\text{CF}_2\text{O})_f(\text{CF}_2\text{O})_g-$
wherein Y is F or CF_3 ; e, f, g are integers such that the molecular weight is within the above mentioned range; e/(f+g) is in the range 0.1-10, f/g is in the range 2-10;

(D) - $(\text{CF}_2(\text{CF}_2)_z\text{O})_s-$
wherein s is an integer such as to give the above mentioned molecular weight, z has the already defined meaning;

(E) - $(\text{CR}_4\text{R}_5\text{CF}_2\text{CF}_2\text{O})_{j'}$, -
wherein R_4 and R_5 are equal to or different from each other and selected from H, Cl or perfluoroalkyl group, for example with 1-4 C atoms, j' being an integer such that the molecular weight is the above mentioned one; said unit inside the fluoropolyoxyalkylene chain can be linked each other as follows:

- $(\text{CR}_4\text{R}_5\text{CF}_2\text{CF}_2\text{O})_{p2} - \text{R}'_f - \text{O} -$
 $(\text{CR}_4\text{R}_5\text{CF}_2\text{CF}_2\text{O})_{q2} -$
wherein R'_f is a fluoroalkylene group, for example from 1 to 4 C, p' and q' are integers such that the molecular weight is the above mentioned one;

(F) - $(\text{CF}(\text{CF}_3)\text{CF}_2\text{O})_{j''}-$
 j'' being an integer such as to give the above mentioned molecular weight.

8. A process according to claims 1-7, wherein the reaction temperature is comprised between 0°C and the boiling temperature of the solvent, preferably between 0°C and 30°C.


9. A process according to claims 1-8, wherein the reducing agent is in an amount in the range 0.1-15% by weight with respect to the solvent weight.

10. A process according to claims 1-9, wherein the organic base amount ranges from 0.1 to 100% by moles with respect to the reducing agent, preferably from 5 to 15% by moles.

11. A process according to claims 1-10, wherein the ex-

cess of reducing agent is in the range 0-30%, preferably 10-20%.

12. A process according to claims 1-11, wherein the hydrolysis (step b) is carried out by adding the reaction product of step a) to an aqueous HCl solution, at a concentration of 5-10% by weight, in equiponderal amount with respect to the initially fed ester; alternatively, by adding water in a ratio by weight 2:1 with respect to the initially fed ester.





(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
21.11.2001 Bulletin 2001/47

(51) Int Cl.7: **C08G 65/32, C08G 65/00**

(43) Date of publication A2:
11.07.2001 Bulletin 2001/28

(21) Application number: **00128069.2**

(22) Date of filing: **21.12.2000**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **04.01.2000 IT MI200003**

(71) Applicant: **Ausimont S.p.A.**
20121 Milano (IT)

(72) Inventors:
• **Tonelli, Claudio**
20099 Sesto S. Giovanni (MI) (IT)
• **Russo, Antonio**
20100 Milano (IT)
• **Strepparola, Ezio**
24047 Treviglio (BG) (IT)

(74) Representative: **Sama, Daniele, Dr.**
Sama Patents
Via Morgagni, 2
20129 Milano (IT)

(54) **A process for the preparation of perfluoropolyoxyalkylenes with hydroxyl end groups**

(57) A process for preparing perfluoropolyoxyalkylenes with hydroxyl end groups having structure:



wherein:

T_1, T_2 , are selected from $-\text{CH}_2\text{OH}$, $-\text{F}$, $-\text{CF}_3$, $-\text{CF}_2\text{CF}_3$ with the proviso that at least one of T_1 and T_2 is $-\text{CH}_2\text{OH}$;
 W_1 and W_2 are selected from F , CF_3 ;
 R_f is a perfluoropolyoxyalkylene chain having a number average molecular weight 500-10,000 comprising one or more units of the type $-\text{CF}_2\text{CF}_2\text{O}-$, $-\text{CF}_2\text{O}-$, $-\text{C}_3\text{F}_6\text{O}-$, $-\text{CF}_2(\text{CF}_2)_z\text{CF}_2\text{O}-$ ($z=1,2$);
 $-\text{CR}_4\text{R}_5\text{CF}_2\text{CF}_2\text{O}-$ with R_4 and R_5 selected from H , Cl , perfluoroalkyl group;

a) adding an ester precursor having structure (I) and T_1, T_2 end groups selected from $-\text{F}$, $-\text{CF}_3$, $-\text{CF}_2\text{CF}_3$, $-\text{COOR}$ (R =linear or branched alkyl group having a number of C atoms from 1 to 5), with the proviso that at least one of T_1 and T_2 is $-\text{COOR}$, in a reaction mixture formed by:

- an inert or protic reaction solvent;
- a reducing agent selected from metal hydrides;
- an unreactive organic base with respect to the ester;

b) hydrolysis of the product obtained in step a) for obtaining the compounds of structure (I) with at least a $-\text{CH}_2\text{OH}$ end group.

said process comprising the following steps:



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 12 8069

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InLCI.7)
A	US 4 094 911 A (MITSCH RONALD ALLEN ET AL) 13 June 1978 (1978-06-13) * column 5, line 8 - line 28 *	1-12	C08G65/32 C08G65/00
A,D	GB 1 309 401 A (MINNESOTA MINING & MFG) 14 March 1973 (1973-03-14) * example 1 *	1-12	
A	US 5 714 637 A (MARCHIONNI GIUSEPPE ET AL) 3 February 1998 (1998-02-03) * example 13 *	1-12	
			TECHNICAL FIELDS SEARCHED (Int.CI.7)
			C08G
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 27 September 2001	Examiner O'Sullivan, T
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention L : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 15/23 (3/82) (FDC01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 12 8069

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-09-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4094911 A	13-06-1978	CA 960222 A2	31-12-1974
		CA 960221 A1	31-12-1974
		CA 960400 A1	31-12-1974
		GB 1309401 A	14-03-1973
		US 3810874 A	14-05-1974
		US 3845051 A	29-10-1974
		US 4085137 A	18-04-1978
		AU 462798 B	10-07-1975
		AU 3317471 A	15-03-1973
		AU 469118 B	05-02-1976
		AU 3317671 A	15-03-1973
		BE 772308 A1	07-03-1972
		BE 772309 A1	07-03-1972
		DE 2145174 A1	23-03-1972
		DE 2145176 A1	16-03-1972
		FR 2106375 A5	05-05-1972
		FR 2116364 A5	13-07-1972
		GB 1373931 A	13-11-1974
		GB 1373932 A	13-11-1974
		JP 1408932 C	24-11-1987
		JP 59191721 A	30-10-1984
		JP 62014169 B	01-04-1987
		JP 1408933 C	24-11-1987
		JP 59191722 A	30-10-1984
		JP 62014170 B	01-04-1987
		JP 60034924 A	22-02-1985
		JP 59191723 A	30-10-1984
		JP 1408934 C	24-11-1987
		JP 59191724 A	30-10-1984
		JP 62014171 B	01-04-1987
		JP 1322347 C	11-06-1986
		JP 59191725 A	30-10-1984
		JP 60050823 B	11-11-1985
		JP 1509565 C	26-07-1989
		JP 62048724 A	03-03-1987
		JP 63061336 B	29-11-1988
		NL 7111865 A	10-03-1972
		NL 7112315 A , B	10-03-1972
		US 3972856 A	03-08-1976
		BE 747087 A1	09-09-1970
		CA 960397 A1	31-12-1974
		DE 2011774 A1	17-09-1970
		DE 2066042 B1	22-11-1979
		FR 2037807 A5	31-12-1970
		GB 1309402 A	14-03-1973
		NL 7002813 A , B,	14-09-1970

EPO FORM P/453

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 12 8069

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-09-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4094911 A		IT 9393 B	
GB 1309401 A	14-03-1973	BE 747087 A1	09-09-1970
		CA 960397 A1	31-12-1974
		DE 2011774 A1	17-09-1970
		DE 2066042 B1	22-11-1979
		FR 2037807 A5	31-12-1970
		GB 1309402 A	14-03-1973
		NL 7002813 A ,B,	14-09-1970
		US 3810874 A	14-05-1974
		US 4094911 A	13-06-1978
		US 3972856 A	03-08-1976
		US 4085137 A	18-04-1978
		JP 51048770 B	22-12-1976
		JP 49020954 B	28-05-1974
US 5714637 A	03-02-1998	IT 1231758 B	21-12-1991
		US 5446205 A	29-08-1995
		US 6156937 A	05-12-2000
		AU 619286 B2	23-01-1992
		AU 3396489 A	25-10-1990
		CZ 8902695 A3	14-06-1995
		DE 68924845 D1	21-12-1995
		DE 68924845 T2	05-06-1996
		EP 0393230 A2	24-10-1990
		ES 2079360 T3	16-01-1996
		IL 90155 A	12-04-1994
		JP 2804077 B2	24-09-1998
		JP 3197436 A	28-08-1991
		KR 184599 B1	15-05-1999
		RU 2034000 C1	30-04-1995
		ZA 8903233 A	28-03-1990

EPO FORM F0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82